

TECHNICAL FEATURES

| | |
|-----------------------|---|
| Trade Name | First eyd emergency eye wash station – French version |
| Use | Emergency eye wash station |
| Material | High impact PS |
| Other features | The directions are clearly printed on the support rack and the bottle can be filled with distilled water or other medicated liquid for ophthalmic use |

DIMENSIONAL FEATURES

| | |
|-------------------|--------------|
| Dimensions | 300 x 300 mm |
|-------------------|--------------|

GENERAL FEATURES

| | |
|----------------|-----|
| CE Mark | Yes |
|----------------|-----|



STERILIZATION (PS)

| | |
|----------------------------------|-----|
| Autoclavability at +121°C | No |
| Gas (Ethylene Oxide) | Yes |
| Dry at 160°C | No |
| Chemical (Formalin) | Yes |
| Radiations | Yes |
| Microwave | No |

CHEMICAL RESISTANCES (PS)

| Categories of substances | Reference | Concentration % | T. 20° C | T. 40° C | T. 60° C |
|---------------------------|------------------|-----------------|----------|----------|----------|
| Inorganic Acid | Sulphuric acid | 98 | C | - | - |
| Organic Acid | Benzoic acid | 100 | B | B | B |
| Alcohol | Ethanol | 100 | B | C | - |
| Aldehydes | Acetaldehyde | 100 | C | - | - |
| Inorganic alkali | Sodium hydroxide | 50 | A | A | A |
| Organic alkali | Aniline | 100 | C | - | - |
| Ketone | Acetone | 100 | - | - | - |
| Esther | Ethyl acetate | 100 | C | - | - |
| Hydrocarbons, halogenated | Dichloroethylene | 100 | C | - | - |
| Hydrocarbons, aromatic | Benzene | 100 | C | - | - |
| Hydrocarbons, linear | Hexane | 100 | C | - | - |
| Supersolvent | Tetrahydrofuran | 100 | C | - | - |

Legenda (not applicable if neglected):

- **A: fair resistance**; exposure (30 days) to the chemical does not cause any damage.
- **B: sufficient resistance**; exposure causes damage of poor importance, which sometimes is only temporary.
- **C: poor resistance**; exposure to chemical is not allowed, or causes immediate permanent damages.

Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing.

Information about resistance of plastic materials to temperatures, steriization and washing treatments are based on bulletins issued by the Producers of raw materials , on literature data and on the experience gained in using the products

PACKAGING

| | |
|------------|--------|
| Box | 10 pcs |
|------------|--------|